



Particle Size Distribution Test Report


IS EN933 – 1: 2012

Washing and sieving

Client Name	Fairways Sands	Scheme / Site	Quality Control
F.A.O.	John Breslin	Material	Sand for Polishing Filters
	Hollywood	Specification	Not Disclosed
	Co Wicklow		

Sample No.	A21694/1	Date Sampled	14/10/2019
Client Ref:	2x Wash	Date Received	14/10/2019
Location	Not Disclosed	Test Commenced	18/10/2019
Lorry Registration	Not Disclosed	Condition of sample as received:	Satisfactory
Docket No.	Not Disclosed	Supplier:	Fairways Sands

Sieve Aperture	% By Mass Passing Sieve
8mm	100
6.3mm	100
5mm	100
4mm	100
2.8mm	100
2mm	99
1mm	71
0.500mm	36
0.250mm	10
0.125mm	1
0.063mm	0.2



Remarks Sampled By Client
 Certificate of sampling where supplied available on request
 Mass of test portion - 992g
 Uniformity Coefficient = 3(Determined in accordance with BS6100 : 1992 : Clause 2.2.1)
 D10 = 0.250mm

Authorized By :
 Michael Quinn **Head of Laboratory** Elsa Fitzpatrick **Production Manager**
 Gerald Roche **Technical / Quality Manager**